

**Manufacturing & Materials Technology,** 37 Graham Road (PO Box 56), Highett, Victoria 3190, Australia Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Web: http://www.cmmt.csiro.au

### Registered Testing Authority - Building Code of Australia

04 April 2007 Our Ref. EN13/1073 03/0211

#### TEST REPORT No. 3834

Requested by: Guardian Tactile Systems

on (date): 15 March, 2007

Manufacturer: Guardian Tactile Systems

Product Desc: Polyurethane Tactile Ground Surface Indicators

Yellow 300 x 300mm Terracotta 300 x 300mm Charcoal 300 x 300mm Ivory 300 x 300mm

Sampling details:

Where: Delivered

Date: 15 March, 2007

By Whom: Client How (methods): N/A

The results reported relate only to the sample(s) tested and the information received. No responsibility is taken for the accuracy of the sampling unless it is done under our supervision. CSIRO cannot accept responsibility for deviations in the manufactured quality and performance of the product. While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results or any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it.

The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 8 pages

### **Executive Summary**

1. Guardian Tactile Systems engaged CSRIO MMT to assess the properties of the polyurethane tactile ground support indicator samples within a defined test program:

ISO 10545-3 Determination of water absorption

AS 4459-4:1997 Determination of modulus of rupture and breaking strength

AS/NZS 4586:2004 Determination of Slip resistance

AS 1428.4-2002 Luminance

AS 1428.4-2002 Design for access and mobility – Tactile indicators

2. The measured outcome of each assessment is stated in the Summary.



**Manufacturing & Materials Technology,** 37 Graham Road (PO Box 56), Highett, Victoria 3190, Australia Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Web: <a href="http://www.cmmt.csiro.au">http://www.cmmt.csiro.au</a>

REPORT NO: 3834 Page 2 of 8

ISSUE DATE: 04 April 2007

MANUFACTURER: Guardian Tactile Systems

PRODUCT DEC: Polyurethane TGSI, 300x300mm

#### **SUMMARY OF TESTS PERFORMED:**

## ISO 10545-3 Determination of water absorption

Water Absorption – ISO10445-3	Tactile				
	Yellow	Terracotta	Charcoal	Ivory	
Average water absorption	0.22%	0.21%	0.02%	0.20%	
Apparent porosity	0.26%	0.26%	0.03%	0.23%	
Apparent relative density	1.19	1.22	1.21	1.17	
Bulb density	1.19	1.22	1.21	1.16	

#### AS 4459-4:1997 Determination of modulus of rupture and breaking strength

Flexural Strength - AS 4459.4	Tactile				
Flexural Strellgth - AS 4459.4	Yellow	Terracotta	Charcoal	Ivory	
Breaking Load (N)	14	16	12	15	
Breaking Strength (N)	13	15	12	14	
Modulus of Rupture (N/mm²)	8.29	9.79	7.70	9.51	
Mean travel length of test arm (mm)	45.0	49.9	49.7	47.3	

The test samples were deformed until they were dislodged from the test apparatus. The test samples did not crack or fracture as a result of the load placed upon them.

#### AS/NZS 4586:2004 Slip resistance of new pedestrian surfaces

	Tactile				
Appendix D, Oil-wet ramp	Yellow	Terracotta	Charcoal	Ivory	
Mean overall acceptance angle:	28.0°	25.7°	28.9°	29.4°	
Classification	R12	R11	R12	R12	



**Manufacturing & Materials Technology,** 37 Graham Road (PO Box 56), Highett, Victoria 3190, Australia Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Web: <a href="http://www.cmmt.csiro.au">http://www.cmmt.csiro.au</a>

REPORT NO: 3834 Page 3 of 8

ISSUE DATE: 04 April 2007

MANUFACTURER: Guardian Tactile Systems

PRODUCT DEC: Polyurethane TGSI, 300x300mm

## **SUMMARY OF TESTS PERFORMED (cont)**

## AS 1428.4-2002 Appendix F - Luminance

Luminance		Tac	tile	
Lummance	Yellow	Terracotta	Charcoal	Ivory
Mean Contrast Dry	49.56	18.25	3.43	66.71
Contrast Range Dry	34.7 – 64.4	12.8 – 23.7	2.4 - 4.5	46.7 – 86.7
Mean Contrast Wet	48.31	16.7	2.21	65.17
Contrast Range Wet	33.8 – 62.8	11.7 – 21.7	1.6 – 2.9	45.6 – 84.7
Contrast Range	33.8 - 64.4	11.7 – 23.7	1.6 – 4.5	45.6 – 86.7

# AS 1428.4-2002 Design for access and mobility – Tactile indicators

Section 2, Clause 2.2.3.3 Design requirements	Requirement
Centre spacing of indicators	50 ±1mm
Direction A	49.89mm
Direction B	49.90mm
Edge to side of indicator	7.5 ±1mm
Direction A	7.99mm
Direction B	7.98mm
Inside warning to warning indicators	15.0 ±1mm
Direction A	14.89mm
Direction B	14.90mm
Height of indicator	4 to 5 mm
Direction A	3.91mm
Direction B	3.91mm
Diameter of indicator upper	25 ±1mm
Direction A	25.19mm
Direction B	24.14mm
Diameter of indicator base	35 ±1mm
Direction A	34.43mm
Direction B	34.51mm

Direction B is at right angles to Direction A



**Manufacturing & Materials Technology,** 37 Graham Road (PO Box 56), Highett, Victoria 3190, Australia Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Web: <a href="http://www.cmmt.csiro.au">http://www.cmmt.csiro.au</a>

REPORT NO: 3834 Page 4 of 8

ISSUE DATE: 04 April 2007

MANUFACTURER: Guardian Tactile Systems

PRODUCT DEC: Polyurethane TGSI, 300x300mm

# DETERMINATION OF WATER ABSORPTION, APPARENT POROSITY, APPARENT RELATIVE DENSITY AND BULK DENSITY

TEST CARRIED OUT IN ACCORDANCE WITH

ISO 105454-3:1995 [Equiv. to AS 4459-3:1999] Test Date 16 March 2007

**RESULTS:** 

Location: Ceramic Tile Laboratory Method: Vacuum

Manufacturer Type: Polyurethane TGSI

#### **Individual Values:**

Tile	Water Abs.(%)	App. Porosity(%)	App. Rel. Density	Bulk Density
Yellow			- 1	
1	0.22 0.26	1.19		1.19
2	0.22 0.26	1.19		1.18
2 3	0.22 0.26	1.19		1.19
4	0.22 0.27	1.19		1.19
5	0.22 0.26	1.19		1.19
Average:	0.22	0.26	1.19	1.19
Terracotta				
1	0.21 0.25	1.21		1.21
2	0.21 0.26	1.22		1.22
2 3	0.21 0.26	1.22		1.22
4	0.21 0.26	1.22		1.22
5	0.20 0.25	1.22		1.21
Average:	0.22	0.26	1.22	1.22
Charcoal				
1	0.02 0.03	1.20		1.20
2	0.02 0.03	1.21		1.21
3	0.02 0.03	1.21		1.21
4	0.03 0.03	1.21		1.20
5	0.03 0.03	1.21		1.21
Average:	0.02	0.03	1.21	1.21
lvory				
1	0.20 0.23	1.17		1.16
2	0.20 0.23	1.16		1.15
3	0.19 0.23	1.17		1.16
4	0.20 0.23	1.17		1.16
5	0.19 0.22	1.17		1.16
Average:	0.20	0.23	1.17	1.16



**Manufacturing & Materials Technology,** 37 Graham Road (PO Box 56), Highett, Victoria 3190, Australia Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Web: <a href="http://www.cmmt.csiro.au">http://www.cmmt.csiro.au</a>

REPORT NO: 3834 Page 5 of 8

ISSUE DATE: 04 April 2007

MANUFACTURER: Guardian Tactile Systems

PRODUCT DEC: Polyurethane TGSI, 300x300mm

#### DETERMINATION OF MODULUS OF RUPTURE AND BREAKING STRENGTH

TEST CARRIED OUT IN ACCORDANCE WITH

AS 4459-4:1997 [Equiv. to ISO 10545-4:1994] Test Date 23 March 2007

**RESULTS**:

Location: Ceramic Tile Laboratory

Work size: Length: 300mm Width: 300mm Thickness: 1.5mm

Number of specimens 3 per colour group

Diameter of rod: 20 mm
Thickness of rubber: 5 mm
Overlap of tile beyond the edge supports: 10 mm
Span of the support rods: 280 mm
Average minimum thickness along ruptures: 1.5mm
Width of the test specimen: 300 mm

Tile	Breaking Load (N)	Breaking Strength (N).	Modulus of Rupture (N/mm²)
Yellow			
1	14.71	14	9.15
2	14.95	14	9.30
3	13.32	12	8.29
Mean	14.32	13	6.42
Terracotta			
1	15.26	14	9.50
2	15.55	14	9.68
3	16.41	15	10.21
Mean	15.74	14	9.80
Charcoal			
1	12.86	12	8.00
2	12.30	12	7.65
3	11.97	11	7.45
Mean	12.38	12	7.70
lvory			
1	14.98	14	9.32
2	16.55	15	10.30
3	14.33	13	8.92
Mean	15.29	14	9.51

The test samples were deformed until they were dislodged from the test apparatus. The test samples did not crack or fracture as a result of the load placed upon them.



**Manufacturing & Materials Technology,** 37 Graham Road (PO Box 56), Highett, Victoria 3190, Australia Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Web: <a href="http://www.cmmt.csiro.au">http://www.cmmt.csiro.au</a>

of 8

Page 6

REPORT NO: 3834

ISSUE DATE: 04 April 2007

MANUFACTURER: Guardian Tactile Systems

PRODUCT DEC: Polyurethane TGSI, 300x300mm

#### **LUMINANCE CONTRAST ASSESSMENT**

TEST CARRIED OUT IN ACCORDANCE WITH

AS 1428.4-2002 (Appendix F) Test Date: 22 March 2007

RESULTS: Location: Slip Resistance Laboratory

Instrument: Gardner Gmbh Color-guide having the following settings

45 °/0° geometry Y x y colour system

Illuminate observer angle of D65/2°

Luminance equation:  $C = \frac{Y_2 - Y_1}{0.5(Y_1 + Y_2)}$ 

No. of samples: 15 readings from 15 random tactile heads.

Assessment		Luminance			
Assessment	Yellow	Terracotta	Charcoal	Ivory	
Mean Contrast Dry	49.56	18.25	3.43	66.71	
Contrast Range Dry	34.7 – 64.4	12.8 – 23.7	2.4 – 4.5	46.7 – 86.7	
Mean Contrast Wet	48.31	16.7	2.21	65.17	
Contrast Range Wet	33.8 – 62.8	11.7 – 21.7	1.6 – 2.9	45.6 – 84.7	
Contrast Range	33.8 – 64.4	11.7 – 23.7	1.6 – 4.5	45.6 – 86.7	



**Manufacturing & Materials Technology,** 37 Graham Road (PO Box 56), Highett, Victoria 3190, Australia Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Web: <a href="http://www.cmmt.csiro.au">http://www.cmmt.csiro.au</a>

REPORT NO: 3834 Page 7 of 8

ISSUE DATE: 04 April 2007

MANUFACTURER: Guardian Tactile Systems

PRODUCT DEC: Polyurethane TGSI, 300x300mm

#### **DETERMINATION OF DESIGN REQUIREMENTS**

TEST CARRIED OUT IN ACCORDANCE WITH AS 1428.4:2002 Clause 2.2.3.3 Design Requirements

Test Date 03 April 2007

**RESULTS**:

Location: Ceramic Tile Laboratory

Number of specimens 1

Measurement	7	Requirement	Direction A (mm)	Direction B (mm)
		(mm)	Mean of six n	neasurements
Centre to centre		50 ± 1	49.89	49.90
Edge to warning indica	tor	7.5 ± 1	7.99	7.98
Inside warning to warn	ing indicators	15 ± 1	14.89	14.90
Edge to warning indica	tor	7.5 ± 1	7.5	7.5
Height base to upper		4 to 5	3.91	3.91
Warning indicator upper	er	25 ± 1	25.19	24.14
Warning indicator base		35 ± 1	34.43	34.51

Direction B is at right angles to Direction A





**Manufacturing & Materials Technology,** 37 Graham Road (PO Box 56), Highett, Victoria 3190, Australia Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Web: <a href="http://www.cmmt.csiro.au">http://www.cmmt.csiro.au</a>

of 8

Page 8

REPORT NO: 3834

ISSUE DATE: 04 April 2007

MANUFACTURER: Guardian Tactile Systems

PRODUCT DEC: Polyurethane TGSI, 300x300mm

Date and Place 04 April 2007 Highett, VIC

Name, Title and Signature

Much.

# **DAVID WEEKS Technical Officer**

Tel: +64 3 92526064 Fax: +64 3 92526244 Email: David.Wee ks@csiro.au