

Materials Science & Engineering, Graham Road (PO Box 56), Highett, Victoria, Australia 3190 Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: http://www.cmse.csiro.au

Registered Testing Authority - CSIRO

28 September 2012

Our Ref. EN13 / 1073 03/0212

TEST REPORT No. 6448s

Requested by:	Guardian Tactile Systems Pty Ltd Unit 11, 88 Erindale Road
	Balcatta
	WA 6021
on (date):	25 September 2012
Manufacturer:	Guardian Tactile Systems Pty Ltd
Product Desc.:	Guardian P.U. Tactile Ground Surface Indicator - Black, 300x300mm
Sompling dotailer	

Delivered
25 September 2012
Courier
N/A

The results reported relate only to the sample(s) tested and the information received. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. CSIRO cannot accept responsibility for deviations in the manufactured quality and performance of the product. While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results of any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it. The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 4 pages

	SUMMARY OF SLIP RESISTANCE TESTS PERFORM	ED:	
		Result	Class
AS/NZS 4586:2004	Slip resistance classification of new pedestrian surface materials		
	Appendix A: WET Pendulum (Four S slider):		
	Mean BPN:	52	W [HIGH*]
AS/NZS 4586:2004	Slip resistance classification of new pedestrian surface materials,		
	Appendix D: OIL-WET Ramp		
	Mean overall acceptance angle:	22.9°	R 11 [MEDIUM*]
* = CSIRO classification			

In order to interpret the classifications, please refer to Standards Australia Handbook 197, An Introductory Guide to the Slip Resistance of Pedestrian Surface Materials, which recommends minimum classifications for a wide variety of locations.

It is important to realise that test results obtained on unused factory-fresh samples may not be directly applicable in service, where proprietary surface coatings, contamination, wear and subsequent cleaning all influence the behaviour of the pedestrian surface.



Materials Science & Engineering, Graham Road (PO Box 56), Highett, Victoria, Australia 3190 Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: http://www.cmse.csiro.au

REPORT NO:6448sPage 2 of 4ISSUE DATE:28 September 2012MANUFACTURER:Guardian Tactile Systems Pty LtdPRODUCT DESC:Guardian P.U. Tactile Ground Surface Indicator - Black, 300x300mm

SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

WET PENDULUM TEST METHOD

RESULTS:	86:2004 (Appe Location:	slip Resista		atony			25 September 2012
RESULIS.	Location.	Silp Resista		atory			ed with grade P400 paper, dry
	Sample: Cleaning: Temperature:	Unfixed Deionized w 23℃	ater				
	Friction Tester: cted by: Andy (N: 0312, c	alibrated 2	6/03/10)		
		Specimen					
		1	2	3	4	5	
Last 3 s	swings	53	52	54	50	51	
	,	53	52	53	49	52	
		53	52	53	50	52	
Average	es	53	52	53	50	52	
-					Ме	an BPN :	52
					CL	ASS :	W [HIGH*]



Materials Science & Engineering, Graham Road (PO Box 56), Highett, Victoria, Australia 3190 Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: http://www.cmse.csiro.au

REPORT NO:6448sPage 3 of 4ISSUE DATE:28 September 2012MANUFACTURER:Guardian Tactile Systems Pty LtdPRODUCT DESC:Guardian P.U. Tactile Ground Surface Indicator - Black, 300x300mm

SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

TEST CARRIED OUT IN ACCORDANCE WITH AS/NZS 4586:2004 (Appendix D)	Test Date: 28 September 2012
Location: Slip Resistance Laboratory	
Sample Fixed	
Joint width: 0 mm	
Surface structure: [] Smooth [] Profiled [X] Structured	
RESULTS	
Mean overall acceptance angle: 22.9 °	
Displacement space: not tested	
CLASSIFICATION:	
Slip Resistance Assessment Group:	R 11 [MEDIUM*]
Displacement Space Assessment Group:	
* = CSIRO classification	

OIL-WET RAMP TEST METHOD



Materials Science & Engineering, Graham Road (PO Box 56), Highett, Victoria, Australia 3190 Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: http://www.cmse.csiro.au

REPORT NO:6448sPage 4 of 4ISSUE DATE:28 September 2012MANUFACTURER:Guardian Tactile Systems Pty LtdTILE DESC:Guardian P.U. Tactile Ground Surface Indicator - Black, 300x300mm

Date and Place

28 September 2012, Highett, Vic

Name, Title and Digital Signature:



ANDY GIANG Technical Officer Tel: 61 3 92526000 Fax: 61 3 92526244 Email: Andy.Giang@csiro.au

*CSIRO recommended classification of Slip Resistance as determined from: AS/NZS 4586: 2004 Slip Resistance Classification of New Pedestrian Surface Materials (Appendices A & D).

Wet Pendulum Class	BPN 4S Rubber	CSIRO Class LOW	CSIRO Class MEDIUM	CSIRO Class HIGH
V	>54	54-57	58-61	>61
W	45-54	45-48	49-51	52-54
Х	35-44	35-38	39-41	42-44
Y	25-34	25-28	29-31	32-34
Z	<25	<18	18-21	22-25
Oil Wet Ramp Class	Angle (degrees)	CSIRO Class LOW	CSIRO Class MEDIUM	CSIRO Class HIGH
R9	≥6 to <10	≥6 to 7.5	7.6 to 9	9.1 to 9.9
R10	≥10 to <19	≥10 to 12	12.1 to 15	15.1 to 18.9
R11	≥19 to <27	≥19 to 21	21.1 to 24	24.1 to 26.9
R12	≥27 to <35	≥27 to 29	29.1 to 32	32.1 to 34.9
R13	>35	>35 to 36	36.1 to 38	≥38.1

AS/NZS 4586 Slip Resistance Classification of New Pedestrian Surface Materials (Appendices A & D).

CSIRO has categorized the AS4586 classifications into sub-groups Low, Medium & High. The slip resistance test classification is still determined according to AS 4586 Australian Standard (Appendices A & D). The added information of Low, Medium and High allows professionals to make a better judgement of pedestrian floor requirements.